

STUCCO - R



LEVELLING PUTTY

DESCRIPTION

STUCCO - R is extremely fine-grained cement based stucco, enforced with special powder resins. It is recommended in leveling and smoothing of interior and exterior surfaces prior the performing of the painting works. It is suitable for walls and ceilings based on plasters, plasterboard and bricks. The mixed product creates a homogeneous, creamy paste with very good workability. It is applied easily and has very good filling properties and performance. It dries fast, it can be easily handled and it doesn't crack nor shrink, giving a superb white, smooth surface.

Application method: Spatoula, plaster trowel or airless spray.

Mixing: About 7, 50 – 8 llt clean water per 20kg STUCCO - R powder. The working life of the mixed product is about 2-3 hours with occasional stirring of the paste without adding water.

Consumption: About 1m²/kg per mm.

Drying times: Touch dry in 1-2 hours, depending on weather conditions (humidity, temperature) and the application thickness of the layer. A Second layer after 3-4 hours can be applied.

Colours: It is available in white.

SURFACE PREPARATION AND PRECESSING

Surfaces must be clean, dry and free from all defective and poorly adhering material, dirt, grease and salts. In case of plasterboards, it is recommended the prior priming of the surface with the Cool Barrier Grip Nano: thinned 50% with water.

Gradually mix in 7, 5-8lt pure water 20kg of STUCCO - R powder, preferably with a mechanical stirrer, until it becomes homogenous. Leave the paste to "calm" for 1-2 minutes. Before the application, stir again the paste without the addition of extra water.

The material is applied with a spatula in 2 or more coats to the final thickness. The final thickness should not exceed the 4 mm. The time between the layers should be not less than 3-4 hours, depending on the temperature and humidity levels of the environment. The final layer can be smoothed with fine sandpaper after 12 hours and then dusted.

The surface should dry thoroughly, before starting any painting works. Prime the dry surface with Cool Barrier Grip primer systems.

The stucco when applied should be allowed to dry at temperatures between 5°C to 35°C. If applied at temperatures above 35°C, before applying, the surface must be poorly wetted with water.

Health and Safety: The product is irritant and contains Portland cement. Before any use read carefully the Material Safety Data Sheet of the product.



Storage - Shelf life: In covered dry place, preferably on pallets at temperatures from 5°C to 40°C, for 12 months since production date.