



COOL BARRIER EPOX ZINC

Product description

This is a two component polyamide cured zinc rich epoxy coating. It is a high zinc dust containing product. It conforms to the compositional requirements of SSPC paint 20, level 2. It provides very good corrosion protection as part of a complete coating system. To be used as primer in atmospheric environments. Suitable for carbon steel, repair of inorganic zinc silicate coating and damaged galvanised steel substrates.

Typical use

Protective:

Suitable for structural steel and piping to be exposed to highly corrosive environments, C5I or C5M (ISO 12944-2). Recommended for offshore environments, refineries, power plants, bridges, buildings, mining equipment and general structural steel. Specially designed as a primer in coating systems where extended durability is required.

Colours

Dark grey,

Product data

Property	Test/Standard	Description
Solids by volume	ISO 3233	53 ± 2 %
Gloss level (GU 60 °)	ISO 2813	matt (0-35)
VOC-EU IED (2010/75/EU) (calculated)		428 g/l
Flash point	ISO 3679 Method 1	27 °C

The provided data is typical for factory produced products, subject to slight variation depending on colour. All data is valid for mixed paint. Gloss description: According to Abolin Performance Coatings' definition.

Film thickness per coat

Typical recommended specification range

Dry film thickness	25 - 125 microns
Wet Film Thickness	45 - 235 microns
Theoretical Speeding Rate	21,0 – 4,2 m ² /l

Surface preparation

To secure lasting adhesion to the subsequent product all surfaces shall be clean, dry and free from any contamination.

Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Carbon steel	Sa 3 (ISO 8501-1)	Sa 2½ (ISO 8501-1)
Shop primed steel	Clean, dry and undamaged approved shop primer (ISO 12944-4 6.1)	Abrasive swept or alternatively blasted to Sa 2 (ISO 8501-1) of at least 70 % of the surface.

Application

Application methods

The product can be applied by

Spray: Use airless spray.

Brush: Recommended for stripe coating and small areas.

Guiding data for airless spray

Nozzle tip (inch/1000) : 15-21

Pressure at nozzle (minimum): 150 bar/2100 psi

Care must be taken to achieve the specified dry film thickness.

Thinner/Cleaning solvent

Thinner: Thinner No. 11

Drying and Curing time

Substrate temperature	5 °C	10 °C	23 °C	40 °C
Surface (touch) dry	50 min	20 min	10 min	5 sec
Walk-on-dry	3 h	3 h	2 h	1 h
Dry to over coat, minimum	3 h	3 h	2 h	1 h
Dried/cured for service	10 d	7 d	5 d	2 d

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product. Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness. Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage. Dry to over coat, minimum: The shortest time allowed before the next coat can be applied. Dried/cured for service: Minimum time before the coating can be permanently exposed to the intended environment/medium.

Induction time and Pot life

Paint temperature	23 °C
Induction Time	30 min
Pot life	24 h

Heat resistance

	Temperature	
	Continuous	Peak
Dry, atmospheric	120 °C	120 °C

Peak temperature duration max. 1 hour.

The temperatures listed relate to retention of protective properties. Aesthetic properties may suffer at these temperatures. Note that the coating will be resistant to various immersion temperatures depending on the specific chemical and whether immersion is constant or intermittent. Heat resistance is influenced by the total coating system. If used as part of a system, ensure all coatings in the system have similar heat resistance.

This Technical Data Sheet supersedes those previously issued.

The Technical Data Sheet (TDS) is recommended to be read in conjunction with the Safety Data Sheet (SDS) and the Application Guide (AG) for this product. ABOLIN CO GREECE: Email: abolin@abolinco.com, web: www.abolinco.com

Date of issue: 11 December 2016

Product compatibility

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product. Some examples are shown below. Contact Abolin for specific system recommendation.

Subsequent coat: polyurethane, epoxy, epoxy mastic

Packaging (typical)

	Volume (litres)	Size of containers (litres)
CB EPOX ZINC Comp A	3	5
CB EPOX ZINC Comp B	1	1

The volume stated is for factory made colours. Note that local variants in pack size and filled volumes can vary due to local regulations.

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life at 23 °C

CB EPOX ZINC Comp A	6 month(s)
CB EPOX ZINC Comp B	48 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

Caution

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Abolin's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Abolin representative for approval before commencing the work.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

Colour variation

When applicable, products primarily meant for use as primers may have slight colour variations from batch to batch. Such products may fade and chalk when exposed to sunlight and weathering.

Disclaimer

The information in this document is given to the best of Abolin's knowledge, based on laboratory testing and practical experience. Abolin's products are considered as semi-finished goods and as such, products are often used under conditions beyond Abolin's control. Abolin cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Abolin reserves the right to change the given data without further notice. Users should always consult Abolin for specific guidance on the general suitability of this product for their needs and specific application practices. If there is any inconsistency between different language issues of this document, the English version will prevail.